

Test Report

Photographic Activity Test according to ISO 18916:2007-06

Summary: The material described below has passed the criteria for enclosure materials defined in ISO 18916:2007 "Photographic activity test for enclosure materials".

PTS Test-Report: 35445
Material description: conservation board 012 natural white - Museumskarton 012 naturweiß

Supplied by: Walter Klug GmbH & Co. KG on 16.02.2022
Zollstraße 2, 87509 Immenstadt

Test Results

1. Image Interaction Test

The material shall not produce a percentage image interaction effect in the colloidal silver fade detectors greater than a relative difference of more than $\pm 20\%$ compared to the control.

Density change of control: -1,25
Density change of material: -1,36 Relative difference: 9%

2. Stain Test

The material shall not produce a mean stain in the photographic paper stain detector that is greater than the mean stain produced by the filter paper controls plus 0.08 density units.

Density change of control: 0,16
Density change of material: 0,18 Difference: 0,02


3. Mottle Test


The enclosure material shall not produce *easily recognizable* mottling.

Visual assessment: **Passed**

Date of testing: 23.03.2022 Sample-ID: 021-07

Papiertechnische Stiftung
Pirnaer Straße 37, D-01809 Heidenau, Germany


Dr.-Ing. Birgit Lutsch
Lab. Manager Materials Testing


Nicole Brandt
PAT Project Manager

Papiertechnische Stiftung is
accredited according to
ISO/IEC 17025.

