

Technical data sheet

Conservation board 086 ES – ivory, multiple ply (thicknesses: 2.5/3.0 mm)



Specifications:

A compact and sturdy ivory solid colour (dyed throughout) conservation board possessing excellent diagonal cutting characteristics. Ideal for conservation-quality picture framing and mounting, displays and museum exhibits.

Sizes ex-stock:

100 x 140 cm

Material characteristics:

Board

- 100% bleached cellulose
- without the usage of recycling fibres
- free of wooden fibres
- Kappa level 1 – 2 = lignin-free
- pH 7.5 - 10.0 = acid-free (in accordance with ISO 6588-1:2020)
- alkaline buffer > 3% natural calcium carbonate (GCC)
- sizing: neutral/synthetic (without alum additive)
- without optical brightening agents
- Photographic Activity Test (PAT) passed in accordance with ISO 18916:2007

Glue used for lamination

- emission-free starch-based adhesive (based on potato starch)
- VOCs-free
- free of solvents and softening agents
- ageing-resistant (permanent)
- pH approx. 7.0
- Photographic Activity Test (PAT) passed in accordance with ISO 18916:2007

This quality corresponds to the technological basis of the following standards:

DIN EN ISO 9706

Information and documentation – Paper for documents – Requirements for permanence

ANSI/ NISO Z.39.48

American National Standard for Permanence of Paper for Publications and Documents in Libraries and Archives

DIN 6738:2007

Highest level of permanency LDK 24-85

Further information, such as our Quality Guarantee, certificates of independent testing institutions and information regarding © KLUG-CONSERVATION, 2024; The information stated in this document is based on our technical knowledge and practical experience. Due to the abundance of possible influences during handling and application, own customer testing is essential. A legally binding guarantee of certain application properties cannot be derived from our technical document, no legal claims can be made on the base of our specifications. Errors and modifications subject to change without notice.

application methods and instructions are stated on our website klug-conservation.com.

