

## Technical data sheet

Binder pocket pages – made from SECOL AS-polyester (75  $\mu$ )



### Specifications:

Transparent SECOL polyester binder pocket pages available in various formats. Made from either AS-polyester or P1-polyester material, 0.075 mm (75 micron) thickness, with standard 4-hole binder-edge. Photographic Activity Test (PAT) passed in accordance with the ISO 18916 norm.

### Sizes ex-stock:

35 mm film negatives, 5 x 5 cm, 6 x 6/6 x 9 slides, 6 x 6 cm, 6 x 7 cm, 9 x 13 cm, 10 x 15 cm, A6, 13 x 18 cm, A5, A4 size

### Material characteristics:

- 60 % polyester
- 40 % polyethylene
- thickness 0.075 mm
- pH neutral
- dimensionally stable
- free of plasticizers (softening agents)
- transparent
- fungus resistant
- melting Point 250-265°C
- water vapour permeability
- flammability, slow to self-extinguishing
- tensile strength 7,36 N/mm
- Tensile tear strength 2800 kg/cm<sup>2</sup> at 25 °C
- Photographic Activity Test (PAT) passed in accordance with ISO 18916:2007

Further information, such as our Quality Guarantee, certificates of independent testing institutions and information regarding application methods and instructions are stated on our website [klug-conservation.com](http://klug-conservation.com).