


Technical data sheet

Corrugated board - EF 2.7 mm - 900 gsm



EF 2.7 mm (item 0211103)



Specifications:

Double corrugated board made of ageing-resistant material, natural white in colour. Flute thicknesses 1.6 and 1.1 mm, total thickness 2.7 mm.

Sizes ex-stock:

 $90 \times 120 \text{ cm}$

Material characteristics:

Base paper

- 100% bleached cellulose
- without the usage of recycling fibres
- free of wooden fibres
- weight 900 gsm
- Kappa level 1 2 = lignin-free
- pH 7.5 10.0 = acid-free (in accordance with ISO 6588-1:2020)
- alkaline buffer > 2% natural calcium carbonate (GCC)
- sizing: neutral/synthetic (without alum additive)
- top surface sizing: Cobb₆₀ in accordance with ISO 535 < 25
- without optical brightening agents
- light-fastness approx. 7-8 (= extremely good) in accordance with the wool scale (EN ISO 105-B02)
- no bleeding in accordance with DIN ISO 16245:2012
- high abrasion resistance in accordance with DIN 53109:2008
- special surface strengthening (dirt-resistant and erasable)
- Photographic Activity Test (PAT) passed in accordance with ISO 18916:2007

Glue used for the corrugated board

- starch-based adhesive
- pH 7.0 8.0

This quality corresponds to the technological basis of the following standards:

DIN EN ISO 9706 Information and documentation – Paper for documents – Requirements for

permanence

DIN ISO 16245 - type A Information and documentation – Boxes, file covers and other enclosures, made

from cellulosic materials, for storage of paper and parchment documents.

NF Z 40-014 Requirements and criteria for selecting paper and cardboard for conserving

paper and parchment documents

[©] KLUG-CONSERVATION, 2024; The information stated in this document is based on our technical knowledge and practical experience. Due to the abundance of possible influences during handling and application, own customer testing is essential. A legally binding guarantee of certain application properties cannot be derived from our technical document, no legal claims can be made on the base of our specifications. Errors and modifications subject to change without notice.

ANSI/ NISO Z.39.48 American National Standard for Permanence of Paper for Publications and

Documents in Libraries and Archives

DIN 6738:2007 Highest level of permanency LDK 24-85

Further information, such as our Quality Guarantee, certificates of independent testing institutions and information regarding application methods and instructions are stated on our website klug-conservation.com.