



Archivability of recycled paper

*Information regarding purchasing paper
for public administration*





ARCHIV

KLUG's expertise

Research for preservation packaging solutions

KLUG-CONSERVATION, with over 150 years of experience, has the know-how to produce premium-quality products made from ageing-resistant paper and board, ensuring maximum permanence and durability for long-term preservation of assets in archives, museums and libraries. Close collaboration with our customers and intense cooperation with the paper industry, research institutes, universities and academies allows us to continually improve our existing products as well as develop new ones. This is essential for maintaining a consistently high quality standard, as well as keeping up-to-date with the latest developments in the conservation field. We would like to share this knowledge with you in the form of our "Technical Knowledge Folders". Should you have any further questions, please refer to our website, our printed publications or contact us personally.

Michael Kühner

Peter Lang

Information regarding purchasing paper for public administration

The public administration attaches great importance to using environmentally friendly paper containing a maximum proportion of recovered paper. Only some of the documents issued on such paper actually end up in the archives for long-term storage. Compliance with the standard EN ISO 9706 is imperative for paper to be considered as long-term ageing resistant.

A position paper on the "Archivability of recycled paper" was published in Germany by the German Environment Agency (Umweltbundesamt – UBA) in February 2014 under the motto "Recycling paper with the Blue Angel is ageing-resistant and promotes a circular economy". The contents of this paper however contradict the arguments advanced nationally and internationally by professional representatives of archives and libraries for decades, while not providing any new insights.

Decomposition of paper – a silent catastrophe

Large proportions of our written cultural heritage are threatened by the silent catastrophe of paper decomposition due to ageing. According to a survey of experts conducted in 2013, cultural artefacts equivalent to a shelf length of approximately 1,500 km are affected in German archives of public bodies and can now only be used to a limited extent or not at all. Reasons for this lie in the composition of industrially manufactured papers and their production methods.

Two “ageing-resistant paper” standards are currently applicable in Germany alone: DIN 6738 and EN ISO 9706 – a material standard. Only EN ISO 9706 is however explicitly dedicated to the “requirements for ageing-resistance” of uncoated paper qualities. In addition to minimum strength properties, this standard states specifications for paper composition regarding alkali reserve and absence of easily oxidised material, i.e. residual lignin and reducible sulfur (Kappa number <5 according to ISO 302:2015). In line with ISO 6588-1:2012, a cold water extract is moreover required to have a pH of at least 7.5.

Representatives of the paper industry, dominated by the DIN Standards Committee Paper, Board and Pulps (NPa 21), developed DIN 6738:2007, which is also intended to position recycled paper in the market. The only criterion quoted by the standard is the stability of strength properties. These are tested after an artificial ageing process (80°C/65% relative humidity) allowing so-called lifespan classes to be derived. According to DIN 6738, papers of the highest lifespan class (LSC 24-85), i.e. those in which at least 85% of the minimum strength properties are retained after an artificial ageing process of 24 days, may be called “ageing resistant”. The standard however explicitly points out that this claimed ageing resistance based on LSC 24-85 “is only fulfilled in case of gentle handling and storage”. It moreover refers to the state of the art according to which “uncoated papers reach this lifespan class if their cold aqueous extract has a pH of 7.5 – 9.5, they are exclusively composed of bleached cellulose and/or rags and have a calcium carbonate content of at least 2% (w/w) (DIN 6738:2007, Note 1)

EN ISO 9706

DIN 6738



The production process causes recycled papers to actually contain a high proportion of easily oxidised substances, such as e.g. lignins, which contribute to a potentially damaging formation of acids. Upper limits for these are only specified by EN ISO 9706. The addition of a high alkaline reserve after all only slows down the acidic hydrolysis of paper. Residual lignin content causes acid to be formed in paper as well as being responsible for fast yellowing and darkening of paper. This is not only detrimental to the legibility of the original, but also to digitalisation and microfilming. The proposal to create a new ISO standard solely dedicated to the “mechanical durability” of paper – with the argumentation that optical properties do not play a role for most applications – was rejected by the Committee for Paper Technology with reference to the applicable EN ISO 9706.

Damage prevention is more economic than repair

No significant difference can be determined when comparing the price of ageing-resistant paper conforming to EN ISO 9706 with recycled papers that do not satisfy this standard. Using unsuitable recycled paper may however lead to high technical, organisational and financial expenditure. A life cycle assessment of so-called “environmentally friendly paper qualities” should furthermore be at least considered.

To make them suitable for long-term archiving, papers with a “Blue Angel” certification first have to be stabilised and possibly even deacidified using a cost-intensive and complicated quantitative method. Depending on the relevant method, the cost of deacidification of a linear meter of shelved archived goods is between EUR 1,000 and EUR 1,300. Apart from the ecological impact of the utilisation of chemicals, the additional costs expected for deacidification of non-ageing-resistant papers would exceed the archives’ budgets for the preservation of stored cultural artefacts by far.



Conclusion!

»Blue Angel« Ageing resistance and EN ISO 9706 are irreconcilable

The requirements of EN ISO 9706 are completely irreconcilable with the demands on recycled paper classified as “environmentally friendly paper” bearing a “Blue Angel” certification. This is because the paper qualities required for the latter have to be composed of 100% recovered paper, as well as contain at least 65% so-called “lower and medium paper grades”. Adequate durability for long-term archiving cannot be expected from such papers, as shown in a study by the Library of Congress in 2014.

Although EN ISO 9706 also permits recovered paper to be used for paper production, the qualities of recovered paper used must be “superior”, e.g. primary fibres from paper manufacturing or recovered paper qualities consisting exclusively of bleached cellulose and/or rags. Such recycled papers cannot however be certified with the “Blue Angel” ecolabel. This hurdle represents a big disadvantage for suppliers in the market who are able to meet the specifications technically, but who do not subject themselves to a “Blue Angel” certification.

Calls for bids stating the “Blue Angel” ecolabel as an exclusion criterion are not permissible by public procurement law.

Conclusion

The only way to prevent the quantity of unique cultural heritage requiring deacidification from increasing further relentlessly is for the public administration to consistently use ageing-resistant papers conforming to EN ISO 9706. Recycled paper that does not fulfil this standard may only be used by administrative bodies or associated organisation units if the papers do not have to be archived. The most effective ecological contribution is of course sparing use of paper at all levels!



References

Position paper of the German Environment Agency (2014). Archivability of recycled paper.

http://papiernetz.de/wp-content/uploads/Umweltbundesamt_Positionspapier_Archivierbarkeit.pdf

Joint position paper by the Conference of Divisional Heads of Archives and Heads of Archive Administrations of the Federation and States (ARK) as well as the Federal Conference of Communal Archives of the Association of German Cities (BKK) (2014). Only paper conforming to EN ISO 9706 fulfils the prerequisites for long-term archiving of written cultural artefacts – Information regarding purchasing paper for public administration.

https://www.bundesarchiv.de/imperia/md/content/bundesarchiv_de/fachinformation/positionspapier_ark_bkk_papier_din_9706_entwurf_09_14.pdf

Archives in the Rhineland – Archive consultation (without year).

A comparison of the paper standards DIN 6738 and EN ISO 9706.

http://www.afz.lvr.de/de/archivberatung/bestandserhaltung_1/vergleich_din_6738_und_din_en_iso_9706/vergleich_der_papiernormen_din_6738_und_din_en_iso_9706.html

EN ISO 9706:2010. Information und documentation – Paper for documents – Requirements for permanence

DIN 6738:2007-03. Papier und Karton – Lebensdauer-Klassen / Paper and paper board – Lifespan classes

DIN – Deutsches Institut für Normung, Berlin: Beuth

ISO 302:2015. Pulps – Determination of Kappa number.

ISO 6588-1:2012. Paper, board and pulps – Determination of pH of aqueous extracts – Part 1: Cold extraction.

Geneva: International Organization of Standardization.

Helen Forde, Jonathan Rhys-Lewis (2013). Preserving archives – Principles and practice in records management and archives. 2nd ed., London: Facet Publishing: p. 11

Library of Congress – Preservation Research and Testing Division (2014). Recycled paper research at the Library of Congress.

https://www.loc.gov/preservation/scientists/projects/rec_paper%20report_2015.pdf

Subscription

Subscribe for the free Technical Knowledge
Folder: klug-conservation.com > Knowledge >
Useful Knowledge



All previously published issues can be found in
our online archive.

KLUG-CONSERVATION
Zollstrasse 2
87509 Immenstadt/Germany
Telephone +49 (0)8323 9653 30
www.klug-conservation.com